

TECHNICAL DATA SHEET

SYNDECK™ 1.5 IMO UNDERLAYMENT (SS1295)

COMMERCIAL LIGHTWEIGHT EPOXY UNDERLAYMENT

SynDeck™ 1.5 IMO Underlayment SS1295 is a three (3) component, aggregate-filled, 100% solids, amine-cured epoxy flooring product that is low odor. It has excellent adhesion and is specifically designed to be 1.5lbs/ft² (7.32kg/m²) at 1/4in (6.3mm) installed. This product can be applied as an underlayment for all approved deck systems. It may also be applied over all approved prime coats. This product meets requirements and has qualifications/certifications for IMO, and Def. Stan. (as part of a system).

Application

SynDeck™ 1.5 IMO Underlayment can be applied to properly prepared or prime coated decks, showers, heads, mess areas, berthing spaces, galleys and passageways. This product is a troweled mixture of epoxy and aggregates designed to be used where irregularities, grades or contours need to be corrected. Good choice in spaces with regular moisture exposure, when underlayment is sealed effectively.

Packaging Description

SynDeck™ 1.5 IMO Underlayment Part A Resin SA1295:

5.2lbs (2.4kg) / .53Gal (2.0L) of product in a 1 Gallon (3.8L) can

SynDeck™ 1.5 IMO Underlayment Part B Hardener SB1295:

1.9lbs (.86kg) / 0.22Gal (0.8L) in a 1 Quart (0.96L) can

SynDeck™ 1.5 IMO Underlayment Part C Aggregate SC1295:

45.0lbs (20.4kg) of aggregate in a bag

Certification & Qualifications

- Meets Parts 2 and 6 of Annex 1 of the IMO FTP Code for primary deck coverings
- Meets Parts 2 and 5 of Annex 1 of the IMO FTP Code for floor coverings
- Meets UK Def Stan 07-247 Annex B, Category A2 (IMO 1.5 1295 [Flexible Resin] system & IMO 1.5 1295 [Epoxy Resin] system)

Benefits

- 100% solids, 0g/L VOC
- Lightweight
- Impact resistance with flexibility

Surface Preparation

Direct to metal: All visible oil, grease, sludge and any other contaminants must be removed prior to mixing and application. SSPC SP11 / ISO 8501-1 ST3 (power tool) at minimum, SSPC-SP10 / ISO 8501-1 SA2.5 (blasting preferable). Surface must be clean, dry, corrosion free, and have a 1-3 mil (25-75 micron) surface profile.

Existing coatings and/or after re-coat window: Light abrasion to achieve a 1-3 mil (25-75 micron) surface profile. Surface must be solvent cleaned, dry, and free of contaminants.

Mixing

Using a mechanical jiffy mixer, mix Part A Resin until a homogenous mixture is obtained. Next, pour Part B Hardener into the premixed Part A Resin. Blend the two components together for 1-2 minutes at a slow to medium speed. Take care not to introduce excessive air into the material. Scrape sides and bottom of container during the mixing process to ensure a completely homogenous mixture.

Carefully transfer Part C aggregate into a large container at least 8 gallons (30 liters). Next, transfer the mixed Part A & B resin blend into the tub. Using a cement-type variable speed mixer with concrete spiral blade, slowly blend components together for 1-2 minutes. Scrape the sides and bottom of tub and continue mixing until all aggregate has been uniformly coated with the resin blend.

SynDeck™

Marine Underlayment and Deck Coatings

SYNDECK™ 1.5 IMO UNDERLAYMENT (SS1295)

COMMERCIAL LIGHTWEIGHT EPOXY UNDERLAYMENT

Properties

Property	Typical Value	Unit
Colors	Tan	
VOC	0	g/L
Mix Ratio	2.4:1.0:25.0	volume
Solids	100	%
Specific Gravity	0.85	
Gloss	Not Applicable	
Abrasion	Not Applicable	
Thinning	None required. Do not thin	
Coverage at 250 mils (6.3mm) WFT	38 3.5	ft ² m ²
Pot Life	30	minutes
Dry time - Tack Free	8-10	hours
Dry time - Light Traffic	12-14	hours
Dry time - Heavy Traffic	Not Applicable	hours
Dry time - Full Cure	5-7	days
Dry time - Recoat Time	Within 24 hours after Tack Free	hours
Clean Up	MEK, Acetone, Denatured Alcohol	
Shelf Life	24 months from date of manufacture	

Product tested at 70°F (20°C) and 50% RH. Pot life, dry time, and recoat times will depend on temperature, humidity and other conditions relative to the environment.

SynDeck™

Marine Underlayment and Deck Coatings

SYNDECK™ 1.5 IMO UNDERLAYMENT (SS1295)

COMMERCIAL LIGHTWEIGHT EPOXY UNDERLAYMENT

Application Methods

Trowel

Apply SynDeck™ 1.5 IMO Underlayment over wet or tacky SynDeck™ Bond Coat SS1222. Use a high quality flat hand trowel to spread material to the desired thickness. Trowel to fair and level deck irregularities and produce positive slopes toward drains. Maximum 2.0in (5.1cm) per application.

Application note:

Pot life is dependent on the size of mixed material. Do not mix more material than can be applied within 30 minutes.

Clean Up

Clean hands and skin with warm water and mild soap.

Clean tools and equipment with MEK, denatured alcohol, or acetone.

Environment

Substrate temperature should be between 50 - 90°F (10 - 32°C). The temperature of the substrate should exceed the "dew point" by 37°F (3°C) during application and hardening. Temperatures should not fall below 41°F (5°C) in the 24 hours after application. Ambient humidity should be between 30 and 70% RH during application and cure.

Storage

Store between 50 - 100°F (10 - 38°C). Keep in a cool, well-ventilated area, away from direct sunlight and heat. Store in a segregated and safe area, avoiding all possible sources of ignition. To maintain stated shelf life and the performance of the product the resins must be kept in original sealed containers at ambient temperature at all times. Avoid low temperature exposure, which may induce adverse effects typical of epoxy materials.

Safety

Refer to SDS for the detailed instruction for safe handling. Use in a well-ventilated area. Do not allow uncured epoxy to be in contact with skin for prolonged periods of time. If contact occurs, wash affected area immediately with soap and water. If eye contact occurs, flush with plenty of warm water. See a physician.

Warranty

The following warranty is made in lieu of all other warranties, either expressed or implied. This product is manufactured of selected raw materials by skilled technicians. Neither seller nor manufacturer has any knowledge or control concerning the purchaser's use of this product and no warranty is made as to the results of any use. The only obligation of either seller or manufacturer shall be to replace any quantity of this product that is proved to be defective. Any claim of defective product must be received in writing within one (1) year from date of shipment. Neither seller nor manufacturer assumes any liability for injury, loss or damage resulting from use of this product.

All reasonable care has been taken to ensure this publication is accurate upon issue. Such information may be affected by changes subsequent to issue. This Technical Data Sheet is to be used solely for this product. Prior to any use, consult the Safety Data Sheet (SDS) for information on hazard risks and product use parameters. All liability and all warranties express or implied are hereby excluded as to product performance results, the accuracy of these data including any warranty of merchantability or fitness for any purpose.SS1295

The logo for SynDeck, featuring the brand name in a bold, black, sans-serif font. The text is centered between two horizontal green bars of equal length.

syndeckmarine.com | 1.877.993.7627 | info@syndeckmarine.com