

TECHNICAL DATA SHEET

SYNDECK™ UNDERLAYMENT SEALER (SS1257)

EPOXY UNDERLAYMENT & GROUT SEALER

SynDeck™ Underlayment Sealer (SS1257) is a two-component epoxy specifically designed to seal underlayments, decks, floors and other porous surfaces. This high thixotropic index material is designed to minimize sag and material loss in areas where higher porosities may be a concern. SynDeck™ Underlayment Sealer provides a sealed surface for additional applications of coatings, sealers and other deck covering materials. This product meets requirements and has qualifications/certifications for IMO and Def. Stan. (as part of a system).

Application

SynDeck™ Underlayment Sealer SS1257 can be applied to seal underlayment decking such as SynDeck™ underlayments such as: Ultra Lightweight Underlayment SS1290FC, Ultra Lightweight underlayment Terrazzo SS1290FCT, ComDeck Epoxy Underlayment SS1271, and 1.5 IMO Underlayment SS1295.

Packaging Description

SynDeck™ Underlayment Sealer Part A Resin SA1257:

5.2lbs (2.4kg) / 0.52Gal (2.0L) of product in a 1 Gallon (3.8L) container

SynDeck™ Underlayment Sealer Part B Hardener SB1257:

1.7lbs (0.77kg) / 0.21Gal (0.80L) in a 1 Quart (0.96L) container

Certification & Qualifications

- Meets parts 2 and 5 of annex 1 of the IMO FTP Code 2010 for Floor Finishes
- Meets UK Def Stan 07-247 Annex B, Category A2 (IMO 1.5 1295 [Flexible Resin] system & IMO 1.5 1295 [Epoxy Resin] system)

Surface Preparation

Direct to metal: This product is not designed for direct to metal application.

Existing coatings and/or after re-coat window: Light abrasion to achieve a 1-3 mil (25-75 micron) surface profile. Surface must be solvent cleaned, dry, and free of contaminants.

Benefits

- 100% solids, 0g/L VOC
- High viscosity & thixotropy
- Trowel & squeegee applied

Mixing

Using a mechanical jiffy mixer, mix Part A Resin until a homogenous mixture is obtained. Next, pour Part B Hardener into the premixed Part A Resin. Blend the two components together for 1-2 minutes at a slow to medium speed. Take care not to introduce excessive air into the material. Scrape sides and bottom of container during the mixing process to ensure a completely homogenous mixture.

Application Methods

Brush

Use top quality stiff bristle brush for best film properties where squeegee cannot be used

Roller

This product is not intended for roller applications

Squeegee

Use high quality stiff blade rubber squeegee

Trowel

Use high quality flat edge trowel

Application note:

Pot life is dependent on the size of mixed material. Do not mix more material than can be applied within 30 minutes.

SynDeck™

Marine Underlayment and Deck Coatings

SYNDECK™ UNDERLAYMENT SEALER (SS1257)

EPOXY UNDERLAYMENT & GROUT SEALER

Properties

Property	Typical Value	Unit
Colors	Clear	
VOC	0	g/L
Mix Ratio	2.5:1 (A:B)	volume
Solids	100	%
Specific Gravity	1.13	
Gloss	Not Applicable	
Abrasion	Not Applicable	
Thinning	None required. Do not thin	
Coverage at 10-12 mils (0.25-0.30mm) WFT	100 - 115 9.3 - 10.7	ft ² m ²
Pot Life	15	minutes
Dry time - Tack Free	4-6	hours
Dry time - Light Traffic	8-12	hours
Dry time - Heavy Traffic	36-48	hours
Dry time - Full Cure	5-7	days
Dry time - Recoat Time	Within 16 hours after Tack Free	hours
Clean Up	MEK, Acetone, Denatured Alcohol	
Shelf Life	18 months from date of manufacture	

Product tested at 70°F (20°C) and 50% RH. Pot life, dry time, and recoat times will depend on temperature, humidity and other conditions relative to the environment.

SynDeck™

Marine Underlayment and Deck Coatings

SYNDECK™ UNDERLAYMENT SEALER (SS1257)

EPOXY UNDERLAYMENT & GROUT SEALER

Clean Up

Clean hands and skin with warm water and mild soap.
Clean tools and equipment with MEK, denatured alcohol, or acetone.

Environment

Substrate temperature should be between 50 - 90°F (10 - 32°C). The temperature of the substrate should exceed the "dew point" by 37°F (3°C) during application and hardening. Temperatures should not fall below 41°F (5°C) in the 24 hours after application. Ambient humidity should be between 30 and 70% RH during application and cure.

Storage

Store between 50 - 100°F (10 - 38°C). Keep in a cool, well-ventilated area, away from direct sunlight and heat. Store in a segregated and safe area, avoiding all possible sources of ignition. To maintain stated shelf life and the performance of the product the resins must be kept in original sealed containers at ambient temperature at all times. Avoid low temperature exposure, which may induce adverse effects typical of epoxy materials.

Safety

Refer to SDS for the detailed instruction for safe handling. Use in a well-ventilated area. Do not allow uncured epoxy to be in contact with skin for prolonged periods of time. If contact occurs, wash affected area immediately with soap and water. If eye contact occurs, flush with plenty of warm water. See a physician.

Warranty

The following warranty is made in lieu of all other warranties, either expressed or implied. This product is manufactured of selected raw materials by skilled technicians. Neither seller nor manufacturer has any knowledge or control concerning the purchaser's use of this product and no warranty is made as to the results of any use. The only obligation of either seller or manufacturer shall be to replace any quantity of this product that is proved to be defective. Any claim of defective product must be received in writing within one (1) year from date of shipment. Neither seller nor manufacturer assumes any liability for injury, loss or damage resulting from use of this product.

All reasonable care has been taken to ensure this publication is accurate upon issue. Such information may be affected by changes subsequent to issue. This Technical Data Sheet is to be used solely for this product. Prior to any use, consult the Safety Data Sheet (SDS) for information on hazard risks and product use parameters. All liability and all warranties express or implied are hereby excluded as to product performance results, the accuracy of these data including any warranty of merchantability or fitness for any purpose.SS1257

The logo for SynDeck, featuring the brand name in a bold, black, sans-serif font. The text is centered between two horizontal green bars of equal length.

syndeckmarine.com | 1.877.993.7627 | info@syndeckmarine.com